

Six10™ Adhesive is a two part epoxy gel adhesive that provides strength and reliability with the convenience of a single part product. The self-metering coaxial cartridge dispenses a gap-filling structural epoxy that bonds tenaciously to wood, metals, fiberglass and concrete. The tube comes with a static mixer that lets you lay down a bead of thickened epoxy with any standard caulking gun.

Six10's shear thinning properties make it "thinner" as it's worked. It can be easily tooled into a non-sagging fillet or used to wet out light to moderate reinforcing fabrics like fibreglass. The hardener provides a long open time but has fast thru-cure. Six10 stays workable in the static mixer for 42 minutes, making it practical for long or complicated assemblies.

Each tube of Six10 comes equipped with a static mixing wand. Additional static mixing wands are available in sets of two (*product number 600-2*)

## MIX RATIO

1 part hardener to 2 parts resin by volume

*Note: Care should be taken when dispensing and mixing. Do not attempt to control the cure time by altering the hardener ratio. Contact ATL Composites for specific information.*

## UNCURED PROPERTIES

	Resin	Hardener
Physical State	Greyish-white Gel	Amber Gel

## CURE CHARACTERISTICS

Pot life -100g @ 25°C (in air)	42 minutes
Minimum recommended temperature	10° C
Cured to a solid state @ 25°C	5-6 hours
Full cure @ 25°C	24 hours
Specific gravity of cured system	1.18
Shore D Hardness - 2 weeks	80
HDT after 2 weeks @ 25°C	52° C

## PACK SIZES

Order Code	PACK
KA610	180 ml
KB610	Box of 6 x180 ml
600-2	Pack of 2 static mixers

## STORAGE

Six10 resin and hardener will keep for 2 years, if kept in original containers at room temperature (15°C to 32°C), and out of direct sunlight. Containers should be tightly sealed to prevent moisture absorption.

## HEALTH AND SAFETY

Six10 resin and hardener have moderate sensitising potential, and should be kept out of the eyes and off the skin.

- Use with good ventilation and adequate safety equipment including impervious gloves and safety glasses.

- If skin contact occurs, remove contaminated clothing immediately, and wash the affected area thoroughly with ATL's 845 hand cleaner and water, avoiding the use of solvents except in the case of massive contamination.

- If eye contact occurs, immediately flush with running water for at least 15 (fifteen) minutes and seek medical advice.

- If swallowed:

Resins - DO NOT induce vomiting, and contact a doctor or the Poisons Information Centre.

Hardeners - DO NOT induce vomiting, give plenty of milk or water and contact a doctor or the Poisons Information Centre.

WEST SYSTEM and Six10 are registered trademarks of WEST SYSTEM Inc.

NOTE Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, nor is protection from law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special or consequential damages. 25/09/13



ATL composites

ATL composites Pty Ltd  
Tel (+61) 7 5563 1222  
Fax (+61) 7 5563 1585  
info@atlcomposites.com  
www.atlcomposites.com